



# Williams Products, Inc

1750 Maplelawn  
 Troy, MI. 48084  
 Toll Free: 800-521-9594 Phone: 248-643-6400  
 Fax: 248-643-7117

## Everlastic® MPP 100 Proplastic

### Description

Isotropic Polyolefin Resilient Molded Foam, White in color

### Uses

Everlastic® MPP 100 Proplastic used with hot or cold applied sealants; Horizontal applications, place Everlastic® MPP 100 Proplastic next to forms; all interrupting columns and objects; adjacent to abutting structures prior to concrete placement. Vertical applications include Everlastic® MPP 100 Proplastic placement between panels, panel to column joints or in block wall joints prior to sealing. Everlastic® MPP 100 Proplastic will also conform to many other uses.

### Sizes

Standard Thickness: 3", 6" (Other sizes skived or laminated).

Widths from 1" to 48".

Self-Stick Pressure Sensitive Adhesive Optional.

Sheet Lengths: 9 LF

### Typical Physical Properties

Property	Test Method	Typical Values
Density (Nominal)	ASTM D-3575	1 PCF
Tear Strength	ASTM D-3575	6 PSI
Compression Strength		
25% Deflection		9 PSI
50% Deflection		15 PSI
Compression Set % @ 25%	ASTM D-3575	8%
Compression Set % @ 50%	ASTM D-3575	25%
Tensile Strength CM	ASTM D-3575	28 PSI
Water Absorption	ASTM D-3575	
(lb./sf of cut surface)		<0.05
K Factor	ASTM C-177	0.24
Service Temperature	PPP C-1752	
Low		-65°F
High		+215°F
Thermal Stability	ASTM D-3575	<0.6
(Change after 24 hrs @ 158°F)		



We do not guarantee the applicability or accuracy of this information or the suitability of our products for any given situation. The products discussed are sold without warranty, expressed or implied. Buyer assumes all responsibility for any loss or damage arising from the handling or use of our products, whether done in accordance with directions or not. Statements concerning the possible use of our products are not intended as recommendations to use our products in the infringement of any patent.