



# Williams Products, Inc

1750 Maplelawn  
 Troy, MI. 48084  
 Toll Free: 800-521-9594 Phone: 248-643-6400  
 Fax: 248-643-7117

## Everlastic® Neoprene Backer Rods

### Description

Extruded and molded closed cell neoprene sponge

### Use

As hot or cold applied sealant backup; to fill vertical and horizontal joints. Resistant to heat, ultraviolet and many chemicals.

Physical Properties		Typical Profiles
ASTM Designation	D-1056-68 D-1056-78 D-1056-85 Suffix Letters	SCE-41 RE-41 2C1 CE1P2MP
MIL R-6130C	Type Grade Condition	II-A Soft
Physical Properties Color	Black	Black (Grey)
Compression-Deflection 25% Defl. (psi) (kN/m <sup>2</sup> )		2-5 (14-35)
Ultimate Tensile Strength (Typical Properties) psi (kN/m <sup>2</sup> )		100 (700)
Elongation (Typical Properties) %		175
Density lb./ft <sup>3</sup> g/cc		7+/-2 0.11+/-0.03
Fluid Immersion, 7 days @ 73°F Ref. Fuel B, weight change max. %		250
Accelerated Aging, 7 days @ 73°F Flexibility 180° bend without cracking Appearance Change Change in compression-defl.		Pass None +/- 30
Maximum Weight %		5
Odor		No Objectionable Odor



We do not guarantee the applicability or accuracy of this information or the suitability of our products for any given situation. The products discussed are sold without warranty, expressed or implied. Buyer assumes all responsibility for any loss or damage arising from the handling or use of our products, whether done in accordance with directions or not. Statements concerning the possible use of our products are not intended as recommendations to use our products in the infringement of any patent.