

# TECH DATA

**Williams Everlastic®**  
**1200 Series**  
**Commercial Grade Dense Neoprene**

## Description

- Dense Rubber
- Color: Black
- Meets ASTM-D 2000

## Available Sizes

- Cut Parts, Rolls & Sheets - CUT TO SIZE
- Cut to Thickness, Width & Length
- Sheet & Roll Sizes vary – call for specific limits
- Available in variable hardness

## Applications

- Bearing Pads
- Vibration Isolation Pads
- Rustification & Chamfer Strips
- Setting Blocks
- Spacers

## Typical Physical Properties

Property	Test Method	Typical Values
Durometer Hardness	ASTM D - 2240	60 ± 5, Shore A
Ultimate Tensile	ASTM D - 412	1000 psi., min.
Ultimate Elongation	ASTM D - 412	300% min.
Ozone Resistance (20% Strain 100 hours @ 104° F)	ASTM D - 1149	No Cracks
Low Temperature Flexibility (5 hours @ -40°F)	ASTM D - 2137	Pass
Aged in Air (70 hrs @ 158°F) Change in Hardness Change in Tensile Change in Elongation	ASTM D - 573	± 15 pts. max. ± 30% max. -50% max. change (not less than 300%)
Compression Set (22 hrs. @ 158° F)	ASTM D -395 Method B	20% max.



We do not guarantee the applicability or accuracy of this information or the suitability of our products for any given situation. Users should make their own tests to determine the suitability of any product for their particular purpose. The products discussed are sold without warranty, either expressed or implied, buyer assumes all responsibility for any loss or damage arising from the handling or use of our products, whether done in accordance with directions or not. Statements concerning the possible use of our products are not intended as recommendations to use our products in the infringement of any patent.